

Application/Control Number : 10/622,636
 Art Unit: 3742
 March 3, 2005
 Page 2

In the Claims.

Please amend the claims as follows:

1. (previously presented) A heated mirror, comprising a glass body on one face whereof a reflective, single-layer film of an electrically conductive metal is deposited by Vacuum Arc Deposition so as to have a thickness of 37-48 nm and to form an actual reflective surface, two conductive busbars being associated with said reflective metal film and being suitable to allow the flow of an electric current in said reflective metal film, the electric current being of 3.5 A or lower upon application of a voltage of 12-13V.
2. (original) The mirror according to claim 1, wherein said glass body is a flat plate.
3. (original) The heated mirror of claim 1, wherein said glass body is curved so that cylindrical, spherical or aspheric mirror shapes are providable.
4. (original) The mirror according to claim 1, wherein said two conductive busbars are interposed between said reflective metal film and said glass body.
5. (original) The mirror according to claim 1, wherein said two conductive busbars are formed directly on said reflective metal film.
6. (original) The mirror according to claim 1, wherein said two conductive busbars are provided by screen printing.
7. (original) The mirror according to claim 6, wherein said screen-printed conductive busbars are provided by means of silver paste.
8. (original) The mirror according to claim 1, wherein said conductive busbars are metal strips arranged on said reflective metal film.
9. (original) The mirror according to claim 8, wherein said metal strips are fixed to said reflective metal film by pressure.
10. (original) The mirror according to claim 1, wherein said reflective metal film is titanium-based.
11. (original) The mirror according to claim 1, wherein said reflective metal film is made of pure titanium.

BEST AVAILABLE COPY

Application/Control Number : 10/622,636
 Art Unit: 3742
 March 3, 2005
 Page 3

12. (original) The heated mirror of claim 1, wherein the ratio between surface resistivity of the reflective film and surface resistivity of the busbars is comprised between 0.8 and 0.9, preferably tending to 1.

13. (original) The mirror according to claim 1, wherein said glass body is chemically tempered.

14. (previously presented) A heated mirror, comprising a glass body on one face whereof a single-layer reflective film of an electrically conductive metal is deposited by Vacuum Arc Deposition so as to have a thickness of 37-48 nm and to form an actual reflective surface with a reflective coefficient of at least 40% and preferably of at least 42%, two conductive busbars being associated with said reflective metal film and being suitable to allow the flow of an electric current in said reflective metal film, and wherein the electric current detectable upon application of a voltage of 12-13 V to said reflective metal film is of 3.5 A or lower.

15.(previously presented) The heated mirror of claim 23, wherein the reflective film has a thickness not higher than 48 nm, and generally as low as 37- 40 nm.

16 . (canceled)

17. (original) The heated mirror of claim 15, wherein the reflective film has a resistivity coefficient $\alpha < 1.5 \times 10^{-3}$.

18. (previously presented) The heated mirror of claim 23, wherein the reflective film is formed by a single, VAD layer which, when supplied with a voltage of 12-13 V, provides a detectable current of 3.5 A or lower.

19. (original) The heated mirror of claim 14, wherein said glass body is curved so that cylindrical, spherical or aspheric mirror shapes are providable.

20. (original) The heated mirror of claim 14, wherein the ratio between surface resistivity of the reflective film and surface resistivity of the busbars is comprised between 0.8 and 0.9, preferably tending to 1.

21. (original) The heated mirror of claim 14, wherein the reflective film is made of pure titanium.

22. (original) The heated mirror of claim 14, wherein the reflective film is made by Vacuum Arc Deposition of titanium doped in the plasma phase.

BEST AVAILABLE COPY

Application/Control Number : 10/622,636
Art Unit: 3742
March 3, 2005
Page 4

23. (previously presented) A heated mirror, comprising a glass body on one face whereof a reflective film of an electrically conductive metal is deposited so as to form an actual reflective surface with a reflective coefficient of at least 40%, and preferably of at least 42%, said film having a preferred thickness that is lower than 48 nm and yielding an electric current of 3.5 A or lower upon application of a voltage of 12-13 V, two conductive busbars being associated with said reflective metal film and being suitable to allow the flow of the electric current in said reflective metal film.

24. (original) The heated mirror of claim 22, wherein the reflective film has a thickness which is generally as low as 40nm.

25. (original) The heated mirror of claim 23, wherein the reflective film has a resistivity coefficient $\alpha < 1.5 \times 10^{-3}$.

BEST AVAILABLE COPY